

材料 Ma a TD5B

特点 F a


高饱和磁感应强度 H Sa a F D

较高的初始磁导率 H l a P ab

低比损耗因子 L R a L Fac


高直流叠加 H DC B a

Bs-Temperature




Initial permeability	μ_i	25°C	4000±25%
Saturation magnetic flux density	Bs(mT)	25°C	550
		100°C	435
Remanent flux density	Br(mT)	25°C	90
		100°C	240
Coercivity	Hc(A/m)	25°C	15
		100°C	21
Relative loss factor	$\tan\delta/\mu_i$	10kHz	< 1.0
	($\times 10^{-6}$)	100kHz	< 2.0
Curie temperature	Tc(°C)		≥ 260

μ_i -Temperature




Electrical resistivity	$\rho(\Omega\cdot m)$
Density	d(kg/m ³)
Test core	Toroid(mm)
	OD : 25
	ID : 15
	H : 7.5

μ_i -Frequency



B-H



μ_i -Frequency

